

- Superior, ablative antifouling protection at an affordable price
- Strong concentration of copper (47.5%)
- Ablative paint film wears away
- Multi-season protection
- Compare to Micron CSC, Cukote, Super-B Ablative, Horizons



Woolsey Yacht Shield is the ablative antifoulant that offers excellent multi-season performance at an affordable price. It performs well in all conditions, including severe fouling waters. A heavy load of copper (47.5%) provides dependable, multi-season performance. Woolsey Yacht Shield's ablative surface wears away with use, exposing fresh biocides while eliminating paint build up and the need for sanding. Can be hauled and re-launched without repainting making it an excellent choice for trailered boats. Woolsey Yacht Shield is the standard ablative antifouling for many boatyards because of its many attributes and favorable pricing.



4802 Blue



4801 Black

Note: Color differences may occur between actual and color chips shown

PHYSICAL DATA	APPLICATION DATA	ASSOCIATED PRODUCTS												
VEHICLE TYPE: Synthetic Polymer/Rosin FINISH: Flat COLORS: 4802 Blue 4801 Black COMPONENTS: 1 CURING MECHANISM: Solvent Release SOLIDS (theoretical): By weight...79 +/- 2% By volume...48 +/- 2% COVERAGE: 400 sq. ft/gal. VOC: 440 g/l max. (as supplied) ACTIVE INGREDIENTS: Cuprous Oxide...47.5% FLASH POINT: 98°F (SETA)	METHOD: Brush, Roller, Airless or Conventional Spray. NUMBER OF COATS: 2 or 3 DRY FILM THICKNESS PER COAT: 2 mils APPLICATION TEMP: 50°F min. / 90°F max. DRY TIME* (HOURS): <table border="1" style="margin-left: 20px;"> <thead> <tr> <th></th> <th>To Recoat</th> <th>To Launch</th> </tr> </thead> <tbody> <tr> <td>90°F</td> <td>3</td> <td>8</td> </tr> <tr> <td>70°F</td> <td>6</td> <td>16</td> </tr> <tr> <td>50°F</td> <td>12</td> <td>48</td> </tr> </tbody> </table> *The above dry times are minimums. Woolsey Yacht Shield may be recoated after the minimum time shown. There is no maximum dry time before launching. THINNER: Pettit 120 Brushing Thinner		To Recoat	To Launch	90°F	3	8	70°F	6	16	50°F	12	48	Pettit 185 Ablative Thinner Pettit 92 Bio-Blue Hull Surface Prep Pettit 95 Fiberglass Dewaxer Pettit 6998 Skip-Sand Primer Pettit 6999 Sandless Primer Pettit 4100/4101 Vivid Epoxy Primer Pettit 4700/4701 High Build Epoxy Primer Pettit 6455/044 Metal Primer Pettit 6627 Tie-Coat Primer Pettit 6980 Rustlok Steel Primer
	To Recoat	To Launch												
90°F	3	8												
70°F	6	16												
50°F	12	48												